

Tork Premium 510 Rulle



Artikel: 510137

System: W1 - Aftørringspapir væg-/gulv-/standardsystem, W3 - Aftørringspapir pakkesystem, W2 - Aftørringspapir kombirullesystem

Lag: 1

Farve: Hvid

Tryk: Nej

Prægning:

Rullebredde: 32 cm

Rullelængde: 152 m

Antal ark: 400

Arklængde: 38 cm

Rullediameter: 25 cm

Produktspecifikation

- Let materiale, så der er plads til rengøring, selvom pladsen er begrænset
- Høj ydeevne under såvel våde som tørre forhold

Forsendelsesdata

Forbrugerenhed:

EAN: 7322540057263

Stk.: 1

Højde: 335 mm

Bredde: 264 mm

Længde: 264 mm

Volumen: 23.3 dm³

Nettovægt: 2675 g

Bruttovægt: 2675 g

Transportenhed:

EAN: 7322540057270

Stk.: 1

Forbrugerenheder: 1

Materiale: Carton

Højde: 335 mm

Bredde: 264 mm

Længde: 264 mm

Volumen: 23.3 dm³

Nettovægt: 2.68 kg

Bruttovægt: 3.03 kg

Miljø

Content

Chemical pulp Polypropene Polyester Chemicals

Material

Chemical pulp Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities. There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free). ECF is based on oxygen, chlorine dioxide and hydrogen peroxide.

TCF is based on hydrogen peroxide and ozone. ECF is used in this product.

Polypropene Polypropene fibre is produced from polypropene resin. The resin is melted in an extruder and spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Polyester** Polyester fibre is produced from terephthalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Chemicals** Both functional and process chemicals are used. The functional chemical used is wet strength agent. The wet strength agent is a polyamide (from polyamidine/epichlorhydrine polymer) with a very high affinity to the fibre. Process chemical used is a surfactant.

Production

This product is produced at Suameer mill, The Netherlands, and certified according to ISO 9001:2000, ISO 14001 and EMAS.

Destruction

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destroyed. The product itself is suitable for incineration. Contact local authorities before destruction.